
**PRODUCT
INFORMATION****NOX-RUST® 110 DLS****Description**

NOX-RUST® 110 DLS is a wax-based, solvent type, cold applied, corrosion preventative designed for use on ferrous and non-ferrous metals when exposed to indoor or outdoor storage conditions. NOX-RUST® 110 DLS deposits a transparent, firm, wax-like film

that is readily removable by conventionally used solvents or degreasing methods. NOX-RUST® 110 DLS is formulated to fulfill the requirements of MIL-C-16173E, Class I, Grade #4 Specification.

Physical Properties**Typical Values**

Appearance

Product:

Film:

Percent Non-Volatiles

Specific Gravity

Pounds per Gallon

Flash Point

Low Temperature Flexibility, -10°F, 90° Bend

VOC

Amber, low viscosity liquid

Non-tacky, amber, wax-like,
transparent film

57% by Weight

0.87

7.3

105°F (Min.)

Pass-no cracking or loss of adhesion.

3.4 lbs./gal. max

Suggested Uses

- Overseas shipments of unpainted metal parts and engine housings, indoor or outdoor, with or without cover.
- Indoor protection of automotive body panels.
- Long-term, general purpose protection of metal parts, dies, tools, and rolls, where an easy-to-remove film is needed.

Protective Properties (Typical Values)

- Outdoor Exposure (Uncovered): 1 Year (Min.)
- Shed Exposure: 5 Years (Min.)
- Salt Spray (ASTM-B-117): 336 Hours (Min.)
- Humidity Cabinets (ASTM-D-1748): 1500 Hours (Min.)

Surface Preparation

The maximum performance of NOX-RUST® 110 DLS can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. Daubert Chemical Company recommends that the metal substrate temperature be 50-95°F (10-35°C) at the time of product application.

Application

NOX-RUST® 110 DLS can be applied by dipping, brushing or spraying. When dipped, the wet applied film thickness ranges from 3.0 to 4.0 and will dry in 1 hour to a film thickness of 1.5 to 2.0 mils. Under these conditions, NOX-RUST® 110 DLS coverage is 700 sq/ft per gallon. NOX-RUST® 110 DLS cures by solvents evaporation. Adequate ventilation is required for cure, and also to prevent the formation of an explosive atmosphere. Further information is provided in the MSDS sheet.

Removal

NOX-RUST® 110 DLS can be removed by using mineral spirits or kerosene-soaked towels. This product can also be removed by vapor degreasing.

Storage

Store NOX-RUST® 110 DLS at temperatures between 50-95°F (10-35°C). Mild agitation is recommended prior to use.

Caution

Adequate ventilation is required for cure and to ensure against formation of a combustible liquid. THE PARTIALLY CURED FILM SHOULD NOT BE EXPOSED TO IGNITION SOURCES SUCH AS FLARES, FLAMES, SPARKS, EXCESSIVE HEAT, OR TORCHES. Refer to Daubert's Material Safety Data Sheet for additional handling and first aid information.

Note:

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus adversely affecting the performance of this coating as stated in the lab data section. If a product other than Daubert Chemical Company's recommended product is required, written authorization must be obtained from Daubert Chemical Company.

February 7, 2012:co

CAUTION: The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

WARRANTY: Daubert Chemical Company, Inc. ("Daubert") warrants all products manufactured by it to be free from defects in material and workmanship. DAUBERT MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY DAUBERT. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Daubert's liability, whether under this warranty or in contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Daubert's option, to the repair or replacement of said products upon their return, transportation prepaid, to Daubert. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL DAUBERT BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES. No Daubert representative or other person is authorized to change this warranty in any way or to assume for Daubert any other liability in connection with the sale or use of its products.

REFER TO MATERIAL SAFETY DATA SHEET FOR HEALTH AND SAFETY INFORMATION.

DAUBERT
CHEMICAL COMPANY, INC.

PAGE 2 OF 2

4700 South Central Avenue ■ Chicago, IL 60638 ■ 1-800-688-0459 ■ or 708-496-7350 ■ Fax: 708-496-7367

Visit our web site at www.daubert.com ■ Our e-mail is dauchem@daubert.com

