
**PRODUCT
INFORMATION****NON-SKID 476B****Description**

NON-SKID 476B is a high performance, heavy duty, abrasion resistant coating composed of synthetic resins and specially selected pigments. NON-SKID 476B will provide a tough, durable exterior coating for steel floors. NON-SKID 476B has excellent adhesion to primed steel and clean surfaces and does not contain any vegetable oils or organic fillers.

Coverage

<u>Wet</u>	<u>Theoretical Dry</u>
50 Sq Ft/Gal @ 32 mils	18 mils
60 Sq Ft/Gal @ 27 mils	15.5 mils
70 Sq Ft/Gal @ 23 mils	13 mils

PHYSICAL PROPERTIES (TYPICAL BATCH)

Color	Black
Weight/Gallon	13.14 ± 0.2 lbs/gal
Flash Point	>100°F
V.O.C.	2.9 lbs/gal

Preferred Surface Preparation

Steel surface to be grit blasted, immediately followed by application of one coat of approved Red Oxide Primer, 1 mil minimum dry film thickness. Apply primer immediately after blasting to prevent any moisture or rust from forming on the clean surface.

Application

NON-SKID 476B may be applied by conventional spray using mastic type 10:1 or 20:1 ratio pumps with a spray tip of 1/4" round, and a 3/4" I.D. hose. Also may be applied by airless spray 30:1 ratio mastic pump with a spray tip of .055:-.065" and a 3/4" I.D. hose. Material may also be rolled onto surface with a 1/8" nap roller.

Drying

NON-SKID 476B will dry tack free under normal drying conditions in about 6 hours. Dries to full hardness in about 48 hours.

June 22, 2010:kc

CAUTION: The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

WARRANTY: Daubert Chemical Company, Inc. ("Daubert") warrants all products manufactured by it to be free from defects in material and workmanship. DAUBERT MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY DAUBERT. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Daubert's liability, whether under this warranty or in contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Daubert's option, to the repair or replacement of said products upon their return, transportation prepaid, to Daubert. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL DAUBERT BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES. No Daubert representative or other person is authorized to change this warranty in any way or to assume for Daubert any other liability in connection with the sale or use of its products.

REFER TO MATERIAL SAFETY DATA SHEET FOR HEALTH AND SAFETY INFORMATION.

DAUBERT
CHEMICAL COMPANY, INC.

PAGE 2 OF 2

4700 South Central Avenue ■ Chicago, IL 60638 ■ 1-800-688-0459 ■ or 708-496-7350 ■ Fax: 708-496-7367

Visit our web site at www.daubert.com ■ Our e-mail is dauchem@daubert.com

