

Tectyl[®] 2502

Sprayable Wood Putty

Description

TECTYL[®] 2502 is a water based wood putty designed to seal joints and cracks in hard wood flooring. When applied to the floor joint of trailers, railroad cars etc., it seals the wood from destructive elements such as rain

ice and road chemicals. Tectyl[®] 2502 will spray through airless equipment. This product can be immediately top coated with Tectyl[®] 2500 latex board coat.

Laboratory Data

Brookfield Viscosity (RV4@10RPM)
Weight/Gallon
VOC LB/GL
Hegman Grind
Percent Solids by Weight
Percent Solids by Volume
Color
Reduction
Substrate
Application
Recommended Dry Film
Cure

Typical Properties

9000 to 12,000 CPS
5.3 +/- 0.2
0.0
6.0 – 7.0
48 ± 2 %
67 ± 2 %
Tan (Wood)
Ready to spray
Oak or Maple Flooring
Airless Spray 15:1, 0.017 tip
N/A
Air Dry 20 to 30 Min

Surface Preparation

The maximum performance of TECTYL[®] 2502 can be achieved only when the surface to be coated is clean and dry. Daubert Chemical Company recommends that the surroundings temperature be 50-95°F (10-35°C) at the time of product application.

Application

TECTYL[®] 2502 is formulated to be used as supplied. Tectyl[®] 2502 does not require thinning, do not add solvent, this is a water base product. This product has been formulated to spray through airless 15:1 pumps with an 0.017 or larger spray tip.

Removal

The dry film is not normally intended for removal. Dried product will be difficult to remove. Equipment must be cleaned immediately after use with warm soap and water.

Storage

Store TECTYL[®] 2502 at temperatures between 50-95°F (10-35°C). Keep container sealed when not in use. Mild agitation is recommended prior to use. **Do not freeze.**

Caution

Adequate ventilation is required for cure and to ensure against formation of a combustible liquid. THE PARTIALLY CURED FILM SHOULD NOT BE EXPOSED TO IGNITION SOURCES SUCH AS FLARES, FLAMES, SPARKS, EXCESSIVE HEAT, OR TORCHES. Refer to Daubert's Material Safety Data Sheet for additional handling and first aid information.

Note:

The addition of any product other than Tectyl[®] 2500 over this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus adversely affecting the performance of this coating as stated in the lab data section. If a product other than Daubert Chemical Company's recommended product is required, written authorization must be obtained from Daubert Chemical Company.

July 7, 2010:kc

CAUTION: The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerable uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

WARRANTY: Daubert Chemical Company, Inc. ("Daubert") warrants all products manufactured by it to be free from defects in material and workmanship. DAUBERT MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY DAUBERT. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Daubert's liability, whether under this warranty or in contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Daubert's option, to the repair or replacement of said products upon their return, transportation prepaid, to Daubert. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL DAUBERT BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES. No Daubert representative or other person is authorized to change this warranty in any way or to assume for Daubert any other liability in connection with the sale or use of its products.

REFER TO MATERIAL SAFETY DATA SHEET FOR HEALTH AND SAFETY INFORMATION.

DAUBERT
CHEMICAL COMPANY, INC.

PAGE 2 OF 2

4700 South Central Avenue ■ Chicago, IL 60638 ■ 1-800-688-0459 ■ or 708-496-7350 ■ Fax: 708-496-7367

Visit our web site at www.daubert.com ■ Our e-mail is dauchem@daubert.com

