
NOX-RUST® VCI-10 OIL**Description**

NOX-RUST® VCI-10 is a volatile corrosion inhibitive lubricating oil for use in the preservation of ferrous metal parts in enclosed systems. Having combined the protective properties of a preservative oil with

those of volatile corrosion inhibitors, NOX-RUST® VCI-10 makes possible long-term protection against rust within what are termed "closed" systems or voids.

**PRODUCT
INFORMATION**

Physical Properties**Viscosity @ 100°F sus****Pour Point****Flash Point****Specific Gravity****Film Thickness @ 77°F****Approximate Coverage****Volatile****Accelerated Corrosion Test, Humidity JAN-H-792, 100%****RH @ 120°F****Vapor Phase Protection, MIL-P-46002A Procedure:****Typical Values****210****-10°F****300°F****0.931****0.5 mils****3000 sq ft per gallon****5%****300 Hours****Pass**

NOX-RUST® VCI-10 is intended for use in the preservation of enclosed systems where the volatile components will provide protection above the oil level. It provides an effective contact preservative oil film. Typical examples of "closed" systems in which NOX-RUST® VCI-10 is used to protect metal from damaging rust include: fuel tanks, storage tanks, cylinders, transmissions, metal containers, gear housings, clutch compartments, crankcases, hydraulic and coolant circulating systems.

Conventional lubricating or preservative oils slushed or fogged into such systems will drain away from the vertical metal surfaces in about six months, exposing the metal to moisture, condensation and corrosion. While NOX-RUST® VCI-10 also drains away, the vaporizing rust inhibitors evolving from the product spread throughout the void or system and neutralize the corrosion-causing tendency of the moisture present in the air. NOX-RUST® VCI-10, being highly fortified with contact inhibitors, also protects the metal below the oil level.

How Nox-Rust® VCI-10 is Used

Since drive clutch and steering clutch assemblies are subject to corrosion within their compartments during shipment and storage, this problem was overcome by fogging three ounces of NOX-RUST® VCI-10 into each chamber and plugging the orifice to retain vapor. Corrosion of hydraulic cylinders can cause leakage. Protection of cylinders and circulating systems is provided by adding 2% NOX-RUST® VCI-10 to the hydraulic test oil. After testing, an additional three ounces are added.

To forestall rust which will foul a diesel injection system, one ounce of NOX-RUST® VCI-10 per each 7 ½ gallons (1 cubic foot) capacity is fogged into the fuel tanks. If tank contains oil or gasoline, one ounce of NOX-RUST® VCI-10 is added for each gallon present.

To protect crankshaft, bearings, rocker arms and all surfaces normally lubricated by crankcase oil, 1% NOX-RUST® VCI-10, by volume, is added to the crankcase oil. To protect upper cylinder walls and valves in diesel or gasoline engines, eight ounces of NOX-RUST® VCI-10 are introduced through the air filter and sucked into the cylinders by turning over the motor with ignition off. For transmissions, 2% NOX-RUST® VCI-10 is added to the lubricant.

The usual properties of NOX-RUST® VCI-10 can be used to advantage for winter layaway of farm and road building equipment and for summer storage of school buses, snow plows, etc. It may also be fogged into shipping cases to protect unpainted auto and truck body sections during shipments.

NOX-RUST® VCI-10 can be used full strength in systems with ferrous metals only. Where non-ferrous metals are present, NOX-RUST® VCI-10 must be diluted to two percent or less, depending on the metals present.

Surface Preparation

The maximum performance of NOX-RUST® VCI-10 can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. Daubert Chemical Company recommends that the metal substrate temperature be 50-95°F (10-35°C) at the time of product application.

Application

NOX-RUST® VCI-10 is formulated to be used as supplied. Ensure uniform consistency prior to use. Continued stirring is generally not required. If the product thickens due to cold storage or loss of solvent during use, contact

Daubert Chemical Company. Daubert Chemical Company recommends that the ambient and product temperature be 50 - 95°F (10 - 35°C) at time of application. NOX-RUST® VCI-10 can be spray or dip applied.

Caution

Adequate ventilation is required for cure and to ensure against formation of a combustible liquid. THE PARTIALLY CURED FILM SHOULD NOT BE EXPOSED TO IGNITION SOURCES SUCH AS FLARES, FLAMES, SPARKS, EXCESSIVE HEAT, OR TORCHES. Refer to Daubert's Material Safety Data Sheet for additional handling and first aid information.

Note:

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus adversely affecting the performance of this coating as stated in the lab data section. If a product other than Daubert Chemical Company's recommended product is required, written authorization must be obtained from Daubert Chemical Company

February 7, 2012:co

CAUTION: The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

WARRANTY: Daubert Chemical Company, Inc. ("Daubert") warrants all products manufactured by it to be free from defects in material and workmanship. DAUBERT MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY DAUBERT. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Daubert's liability, whether under this warranty or in contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Daubert's option, to the repair or replacement of said products upon their return, transportation prepaid, to Daubert. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL DAUBERT BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES. No Daubert representative or other person is authorized to change this warranty in any way or to assume for Daubert any other liability in connection with the sale or use of its products.

REFER TO MATERIAL SAFETY DATA SHEET FOR HEALTH AND SAFETY INFORMATION.

DAUBERT
CHEMICAL COMPANY, INC.

PAGE 2 OF 2

4700 South Central Avenue ■ Chicago, IL 60638 ■ 1-800-688-0459 ■ or 708-496-7350 ■ Fax: 708-496-7367

Visit our web site at www.daubert.com ■ Our e-mail is dauchem@daubert.com

