
V-DAMP® 3771G
Sound Deadener**PRODUCT
INFORMATION**

V-DAMP® 3771G is a viscoelastic, sprayable liquid sound damper. It has been found to be highly effective in reducing vibrational resonance conditions in structures such as stainless steel sinks and other plumbing fixtures, sheet metal panels, floor housings, and a multitude of other applications. V-DAMP® 3771G dissipates structure-borne vibrational energy and reduces radiated air-borne noise.

Waterbased and non-toxic, V-DAMP® 3771G offers an efficient and effective alternative to solvent-based sprayable damping products, as well as sheet applied damping materials. V-DAMP® 3771G can be sprayed or brushed directly from the drum without thinning. After application, V-DAMP® 3771G cleans up with water.

A typical setup to spray V-DAMP® 3771G consists of a 30:1 airless pump, a reverse-a-clean airless gun with a tip size of 0.021", a ram and a surge tank.

V-DAMP® 3771G exhibits exceptional adhesion to a variety of materials when properly applied, and air-dries within 24 hours at room temperature. The drying time can be accelerated through oven drying using moderate temperatures.

KEY ATTRIBUTES OF V-DAMP® 3771G

- Sound Deadening Properties – OBERST BAR (SAE J-1637) METHOD - Composite Loss Factor of 0.070 @ 270 Hz, 77 °F. Steel thickness 32 mils (0.8 mm). Coating thickness 32 mils (0.8 mm).
- Cold adhesion – when V-DAMP® 3771G is applied to a 10" x 10" x .035" panel of primed cold rolled steel at the rate of 0.5 lbs./sq. ft. (dry weight), shows no loss of adhesion when subjected to two 25" lb. impacts from a two inch diameter, 1 ¼ lb., steel ball at -20°F.

APPLICATION

Surface must be clean and free of oil and foreign matter. Adhesion is very good on stainless steel, bonderized steel, primed steel, wash-primed galvanized sheet metal, and wash-primed aluminum. Airless spray mastic type equipment is recommended for application.

Airless Spray - 0.021" to 0.037" spray tip, ½" i.d. material hose, a Graco Bulldog® Pump 30:1 ratio or higher.

DRYING

20 mils wet film at room temperature dries hard in 2-3 hours.

32 mils wet film at room temperature dries hard in 4-6 hours.

Where faster drying time is required, use forced ventilation, heat or infrared light.

THINNING

Product is ready for use as received. If conditions should require thinning, use water sparingly.

CLEAN-UP

After use, equipment may be flushed with water.

PHYSICAL PROPERTIES (TYPICAL)

Color	Light Gray
Viscosity	Brookfield RV, #7 @20 55,000 cps
Solids by Weight	60%
Solids by Volume	41%
Weight/Gallon	12.1
Flash Point	None
VOC (EPA Method #24)	0 lbs./gal. (water-based coating)
Non-Bleeding	Non-Asphaltic
Odor After Drying	None
Chemical Resistance	Resistant to dilute acids, alkali, grease, gasoline, and aliphatic oils.
Latex Emulsion	Protect From Freezing

Note: V-DAMP® 3771G is not intended for direct outdoor weathering. The outdoor weathering resistance of V-DAMP® 3771G can be improved by painting with a latex exterior paint.

CONSULT MSDS BEFORE USE.

June 22, 2010:kc

CAUTION: The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

WARRANTY: Daubert Chemical Company, Inc. ("Daubert") warrants all products manufactured by it to be free from defects in material and workmanship. DAUBERT MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY DAUBERT. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Daubert's liability, whether under this warranty or in contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Daubert's option, to the repair or replacement of said products upon their return, transportation prepaid, to Daubert. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL DAUBERT BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES. No Daubert representative or other person is authorized to change this warranty in any way or to assume for Daubert any other liability in connection with the sale or use of its products.

REFER TO MATERIAL SAFETY DATA SHEET FOR HEALTH AND SAFETY INFORMATION.

DAUBERT
CHEMICAL COMPANY, INC.

PAGE 2 OF 2

4700 South Central Avenue ■ Chicago, IL 60638 ■ 1-800-688-0459 ■ or 708-496-7350 ■ Fax: 708-496-7367

Visit our web site at www.daubert.com ■ Our e-mail is dauchem@daubert.com

